

LOW-TEMPERATURE PRESS PROCESS FOR MAKING INSULATING GLASS ASSEMBLIES

ABSTRACT

5 A process for making an insulating glass assembly is disclosed, the process
including applying a sealant composition to a surface of a spacer; contacting the sealant
composition with a glass pane, and applying pressure on the glass pane to bond the glass
pane to the spacer through the sealant composition, the pressure being applied at an
ambient temperature of from about 15°C to about 60°C.

10